

FLORATECH[®] ASIA
 6 FL., NO. 360, RUEI GUANG ROAD
 NEIHU, TAIPEI, TAIWAN, ROC
 PHONE: 886 2 8751 6060
 FAX: 886 2 8751 6363

FLORATECH[®] AMERICAS
 291 EAST EL PRADO COURT
 CHANDLER, ARIZONA 85225
 PHONE: 480-545-7000
 FAX: 480-892-3000

FLORATECH[®] EU
 VIA TANARO 15, 20017 RHO
 MILAN, ITALY
 PHONE: 39 02 93 04946
 FAX: 39 02 93 50 8238

see www.floratech.com to find your local Floratech representative

Pot Lip Gloss

Products highlighted: Floraesters[®] 30, Floraesters 60 and Floraesters 70

This luxurious, tinted lip gloss adds shine and color while protecting the lips from sun and wind.

Phase	Trade Name	INCI Name	Supplier	%wt./wt.	
A.	Floraesters 30	Jjoba Esters (and) Tocopherol	Floratech	1.00	
	Floraesters 60	Jjoba Esters (and) Tocopherol	Floratech	1.60	
	Floraesters 70	Jjoba Esters	Floratech	5.00	
	Fluilan	Lanolin Oil	Croda	Q.S.	
	Indopol H-100	Polybutene	Amoco Chemical	16.00	
	Bentone Gel LOI	Lanolin Oil (and) Isopropyl Palmitate (and) Stearalkonium Hectorite (and) Propylene Carbonate (and) Propylparaben	Elementis Specialties	13.00	
	Covi-Ox T-70	Tocopherol	Cognis	0.02	
	Cetiol LC	Coco-Caprylate/Caprata	Cognis	0.01	
	Carnauba Wax #1 Yellow SP 63	Copernicia Cerifera (Carnauba) Wax	Strahl & Pitsch	2.00	
	Candelilla Wax SP 75	Euphorbia Cerifera (Candelilla) Wax	Strahl & Pitsch	1.80	
	Preservative	-----		Q.S.	
	Parsol MCX	Ethylhexyl Methoxycinnamate	DSM	3.00	
	Petrolatum White	Petrolatum	Penreco	2.50	
	B.	D&C Red No. 7 Calcium Lake	Red 7 Lake	Sensient Food Colors	0.50
		FD&C Yellow No. 5 Al. Lake	Yellow 5 Lake	Sensient Food Colors	1.10
Titanium Dioxide		Titanium Dioxide	Sensient Food Colors	0.50	
FD&C Blue No. 1 Al. Lake		Blue 1 Lake	Sensient Food Colors	0.03	
FD&C Red No. 21		Red 21	Sensient Food Colors	0.10	
C.	Titanium Dioxide and Mica	Titanium Dioxide (and) Mica	Mearl	3.00	
D.	Flavor/Fragrance	Flavor/Fragrance		Q.S.	
			TOTAL	100.00	

Mixing Procedure:

1. Combine and heat Phase A to 85°C with agitation.
2. Mill Phase B into a portion of Phase A.
3. Mix Phase B (milled) into Phase A. Add Phase C and mix until uniform.
4. Add Phase D and mix until uniform.

Note: The information herein is based on our research and the research of others and is believed to be accurate. No guarantee of their accuracy is made and the products discussed are sold without warranty, expressed or implied, and upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes. Likewise, statements concerning the possible use of these products are not intended as recommendations to use these products in infringement of any patent.